

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-081533

(43)Date of publication of application : 27.03.2001

(51)Int.Cl.

C22C 38/00

C21D 9/46

C22C 38/14

C22C 38/58

(21)Application number : 11-261879

(71)Applicant : SUMITOMO METAL IND LTD

(22)Date of filing : 16.09.1999

(72)Inventor : NOMURA SHIGEKI
NAKAGAWA HIROYUKI

(54) HIGH TENSILE STRENGTH COLD ROLLED STEEL SHEET AND ITS MANUFACTURE

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a high tensile strength cold rolled steel sheet having ≥ 980 N/mm² tensile strength and low yield ratio and excellent in elongation, bendability, and delayed fracture characteristics.

SOLUTION: The cold rolled steel sheet has a composition containing 0.10-0.20% C, $\leq 0.8\%$ Si, 1.6-2.7% Mn, $\leq 0.03\%$ P, $\leq 0.010\%$ S, 0.005-0.10% Al, 0.0020-0.0080% N, and $[48/14N(\%)+0.005]$ to 0.12% Ti and further containing, if necessary, proper amount of one or more kinds among Cr, Mo, Nb, V, B, Ca, Cu and Ni and also has a structure containing ferrite, martensite, and austenite, each having ≤ 5 μ m grain size, in the prescribed proportion. At manufacture, the cold rolled steel sheet of specific composition is heated up to a temperature determined in view of the composition, cooled from 600-750° C down to 200-420° C at a rate of (10 to 200)° C/s, held in the temperature region for 80 s to 5 min, and cooled down to room temperature to undergo annealing treatment.